

Sklená tkanina Potiahnutá
PTFE

Glasgewebe PTFE-
beschichtet

Glass Fabric PTFE
coated

GF



Technické Dáta

Technische Daten

Technical Data

SLAVBIZ

Predaj a distribúcia PTFE teflonovej fólie

Dušan Magyar-SLAVBIZ
Novomestská 42/39, 926 01 Sered'
Tel.: +421 905 203 396
Email: slavbiz@gmail.com
Web: www.slavbiz.sk

Typ/Číslo výrobku Style/article-no. Typ-/Artikel-Nr	PTFE (%) PTFE (%) PTFE (%)	Hmotnosť (g/m ²) Weight (g/m ²) Gewicht (g/m ²)	Nominálna hrúbka (mm) Nominal thickness (mm) Nominale Stärke (mm)	Štandardná šírka (mm) Standard widths (mm) Standardbreiten (mm)	Pevnosť v ťahu (N/5cm) Tensile strength (N/5cm) Dehnbarkeit (N/5cm)
---	----------------------------------	---	---	---	---

Teplota (°C) Temperature (°C) Temperatur (°C)

- 170 / + 260

68.296.15LAM	63	296	0,15	1000	1800
68.115.08	68	155	0,08	1000	800
60.270.13	60	270	0,13	1000	1200
65.316.15	65	316	0,15	1000	1200
62.530.25	62	530	0,25	1000, 2000, 2600	2300
66.580.28	66	580	0,28	1000	2300
59.720.36	59	720	0,36	1000, 1500, 2000	3500
64.135.08	64	135	0,075	1000, 1300	800
58.255.13	58	255	0,125	1000, 1500	1200
63.296.15	63	296	0,14	1000	1200
59.490.23	59	480	0,23	1000, 1500	2300
55.650.33	55	650	0,33	1000, 1500, 2000, 2600	3500
53.107.08	53	107	0,07	1000	800
48.220.13	48	220	0,11	1250	1200
54.235.13	54	235	0,115	1000, 1500	1200
60.276.15	60	276	0,13	1000	1200
55.455.25	55	455	0,22	1000, 1500	2300
68.155.08AS	68	155	0,08	1000	800
54.235.13AS	54	235	0,115	1000	1200
58.255.13AS	58	255	0,125	1000	1200
63.296.15AS	63	296	0,14	1000	1200
55.455.25AS	57	470	0,23	1000, 1500	2300
58.490.25AS	58	490	0,24	1000, 1500	2300
60.520.25AS	60	520	0,25	1000, 2000, 2600	2300
56.670.35AS	56	670	0,35	1000, 1500, 2000, 2600	3500
64.135.08TR	64	135	0,075	1000	980
57.255.13TR	57	255	0,14	1000	1800
61.285.15TR	61	285	0,15	1000	1800
55.455.25TR	55	455	0,23	1000	2800
57.255.13TR	57	255	0,14	1000	1800

Top Sériá

Prémiová séria

Štandardná séria

Priemyselná séria

Čierna anti-
statická séria

Odolná voči
roztrhnutiu